




# DOWANOL EPh

## Ethylene Glycol Phenyl Ether



**A slow-evaporating glycol ether with high polymer solvency and excellent coalescing abilities; specifications meet needs for cosmetics, cleaners, and textile processing**

### Introduction

DOWANOL\* EPh glycol ether is an aromatic, slow-evaporating glycol ether. It can be used in dyeing synthetic fibers, both as a dye solubilizer and as a dye carrier. DOWANOL EPh glycol ether is also a very efficient coalescing agent. It finds additional uses in cosmetics and cleaning products.

### Physical properties<sup>†</sup>

Molecular weight (g/mol)		138.2
Boiling point @ 760 mmHg, 1.01 bar	471°F	244°C
Flash point (Setaflash Closed Cup)	250°F	121°C
Freezing point	54°F	12°C
Vapor pressure @ 20°C — extrapolated		0.004 mmHg 0.006 mbar
Specific gravity (25/25°C)		1.109
Density @ 20°C	9.26 lb/gal	1.110 g/cm <sup>3</sup>
@ 25°C	9.23 lb/gal	1.106 g/cm <sup>3</sup>
Viscosity (cP or mPa·s @ 25°C)		21.5
Surface tension (dynes/cm or mN/m @ 25°C)		42.0
Specific heat (J/g°C @ 25°C)		2.20
Heat of vaporization (J/g) at normal boiling point		376
Net heat of combustion (kJ/g) — predicted @ 25°C		29.1
Autoignition temperature	923°F	495°C
Evaporation rate	(n-butyl acetate = 1.0) (diethyl ether = 1.0)	0.001 >1200
Solubility, g/100 g @ 25°C		
Solvent in water		2.5 (2.5 wt %)
Water in solvent		10 (9 wt %)
Hansen solubility parameters (J/cm <sup>3</sup> ) <sup>1/2</sup>		
δ <sub>d</sub> (Dispersion)		17.8
δ <sub>p</sub> (Polar)		5.3
δ <sub>h</sub> (Hydrogen bonding)		12.3
Flammable limits (vol.% in air)		
Lower		0.95
Upper		—

<sup>†</sup> The physical property data listed here are considered to be typical properties, not specifications.

### Classification/Registry Numbers<sup>††</sup>

CAS Number	122-99-6
AICS (Australia)	122-99-6
DSL (Canada)	122-99-6
ECL (Korea)	3-2898
EINECS (EU)	204-589-7
MITI (Japan)	3-558
TSCA (U.S.)	122-99-6

<sup>††</sup> **NOTE:** Classifications apply only to this glycol ether product. It is the responsibility of the formulator to ensure that the final finished product complies with the regulations of a given country prior to its sale or distribution in that country.

*(Please see reverse side)*

# DOWANOL EPh

## Ethylene Glycol Phenyl Ether

### Suggested applications

- Latex coalescent in water-based architectural and industrial coatings.
- Solvent and plasticizer for nitrocellulose, cellulose acetate, ethyl cellulose, and many vinyl, phenolic, alkyd, and ester-type resins in water-based coatings.
- Solvent in printing inks.
- Carrier solvent for textile dyes.
- Emulsifier to help lower interfacial tension in oil-water emulsions.
- Ingredient in slurring compounds used to protect metal surfaces against corrosion.
- Intermediate for bactericidal agents.
- Coalescent for latex adhesives.
- Paint removers.
- Cosmetic ingredient.
- Perfume fixative.

### Features

- Coalescing ability
- High polymer solvency
- Low evaporation rate
- Wide range of applications

NOTE: Consult the appropriate Material Safety Data Sheet for safety and handling guidelines for this product.

**The Dow Chemical Company  
Midland, Michigan 48674 U.S.A.**

**In The United States And Canada: 1-800-447-4369; Fax: 1-989-832-1465**  
**In Europe: +800 3 694 6367; Toll Phone: +32 3 450 2240; Toll Fax: +32 3 450 2815**  
**In The Pacific: +852 2879 7260; Fax: +852 2827 5881**  
**In Other Global Areas: 1-989-832-1556; Fax: 1-989-832-1465**

**Notice:** No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

Published August 2001

